

Technical Data Sheet – TopGreen® Co-polyester film

SHFTU is a co-polyester film with excellent uniformity of thickness and stable shrinking behaviors. SHFTU is a high TDO shrink film with good MDO shrink performance. It is suitable for high contour containers. Use steam tunnel for best shrink performance.

Properties		Unit	Spec.	Test Method
Thickness		µm	25 - 80	ASTM D 1400
Shrinkage	TD	%	77 ± 5 1.2 ± 1.5	FENC Method (95°C, 10 Sec. in water)
	MD			
Tensile strength	TD	PSI	40000 ± 8000 9000 ± 1500	ASTM D-882
	MD			
Haze		%	3 ± 2	ASTM D-1003
Gloss @ 60°degrees		%	145± 20	ASTM D-523
Coefficient of friction (US/UK)			0.41±0.07 / 0.35±0.07	ASTM D 1894
Density		g/cm ³	1.32	
Material yield	40 µm	m ² /kg	18.94	ASTM D-1505
	45 µm		16.83	
	50 µm		15.15	
Storage	Do not expose to direct sunlight, store below 86F (30°C) and above 50F (10C)			

